

საქართველოს სტანდარტი

გეოსინთეტური ბარიერები - სატრანსპორტო ინფრასტრუქტურაში
გამოყენებისთვის მოთხოვნილი მახასიათებლები

საქართველოს სტანდარტებისა და მეტროლოგიის
ეროვნული სააგენტო
თბილისი

საინფორმაციო მონაცემები

1 შემუშავებულია საქართველოს სტანდარტების და მეტროლოგიის ეროვნული სააგენტოს სტანდარტების დეპარტამენტის მიერ

2 დამტკიცებულია და შემოღებულია სამოქმედოდ საქართველოს სტანდარტების და მეტროლოგიის ეროვნული სააგენტოს 2018 წლის 29 აგვისტოს № 86 განკარგულებით

3 მიღებულია გარეკანის თარგმნის მეთოდით სტანდარტიზაციის ევროპული კომიტეტის სტანდარტი ენ 15382:2013 „, გეოსინთეტური ბარიერები - სატრანსპორტო ინფრასტრუქტურაში გამოყენებისთვის მოთხოვნილი მახასიათებლები“

4 პირველად

5 რეგისტრირებულია საქართველოს სტანდარტების და მეტროლოგიის ეროვნული სააგენტოს რეესტრში: 2018 წლის 29 აგვისტო №268-1.3-014015

აკრძალულია ამ სტანდარტის გადაცემა მესამე პირებისათვის ან/და მისი სხვა ფორმით გავრცელება

July 2013

ICS 59.080.70; 93.080.20

Supersedes EN 15382:2008

English Version

Geosynthetic barriers - Characteristics required for use in transportation infrastructure

Barrières géosynthétiques - Caractéristiques requises pour l'utilisation dans l'infrastructure des voies de transport

Geosynthetische Dichtungsbahnen - Eigenschaften, die für die Anwendung in Verkehrsbauden erforderlich sind

This European Standard was approved by CEN on 16 May 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms, definitions and abbreviations	8
3.1 Terms and definitions	8
3.2 Abbreviations	8
4 Required characteristics and corresponding methods of test	9
4.1 General	9
4.2 Types of applications	9
4.3 Relevant characteristics	11
4.4 Characteristics relevant to specific conditions of use	16
4.4.1 General	16
4.4.2 Tear strength	16
4.4.3 Friction characteristics (direct shear and inclined plane tests)	16
4.4.4 Chemical resistance	16
4.4.5 Low temperature behaviour	16
4.4.6 Weathering	16
4.4.7 Resistance to wetting and drying	17
4.4.8 Freeze-thaw cycle resistance	17
4.4.9 Resistance to root penetration	17
4.5 Release of dangerous substances	17
5 Evaluation of conformity	17
5.1 General	17
5.2 Verification of values	18
5.3 Initial type tests	18
5.4 Factory production control	19
5.5 Inspection	19
6 Marking	19
Annex A (normative) Factory production control — Factory production control scheme	20
A.1 General	20
A.2 Product design	20
A.3 Production	20
A.3.1 Raw or incoming materials	20
A.3.2 Production process	20
A.4 Finished products	20
A.4.1 Raw or incoming materials	20
A.4.2 Alternative tests	23
A.4.3 Equipment	23
A.5 Provisions applicable to A.2, A.3 and A.4 (to be used where appropriate)	24
A.5.1 Records	24
A.5.2 Assessment of results	24
A.5.3 Traceability	24
A.5.4 Corrective action for non-conforming materials and products	24
A.5.5 Personnel	24
A.5.6 Quality management	24
Annex B (normative) Durability of geosynthetic barriers	25
B.1 Introduction	25
B.1.1 Standards to which this annex is common	25
B.1.2 Mechanisms of degradation	25
B.1.3 Service life	26

B.1.4	Use of rework materials	26
B.2	Test requirements.....	26
B.2.1	General requirement.....	26
B.2.2	Requirements for repeat testing	26
B.2.3	Requirements for individual materials	27
B.3	Durability tests.....	28
B.3.1	Introduction	28
B.3.2	Weathering	28
B.3.3	Resistance to micro-organisms	30
B.3.4	Resistance to environmental stress cracking	30
B.3.5	Resistance to leaching.....	30
B.3.6	Resistance to oxidation	31
B.3.7	Chemical resistance	31
B.4	Evaluation tests and acceptance criteria	31
B.4.1	General.....	31
B.4.2	Evaluation by comparison of tensile properties	31
B.4.3	Evaluation by comparison of Oxidative Induction Time (OIT) values.....	32
B.4.4	Evaluation by change in mass	32
B.4.5	Evaluation by change in water permeability.....	32
	Annex C (informative) Major technical changes to previous edition.....	33
	Annex ZA (informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Directive	34
ZA.1	Scope and relevant characteristics	34
ZA.2	Procedure for the attestation of conformity for geosynthetic barriers used in transportation infrastructure	35
ZA.2.1	Systems of attestation of conformity	35
ZA.2.2	Certificate and declaration of conformity	36
ZA.3	CE marking and labelling.....	37
	Bibliography	41

Foreword

This document (EN 15382:2013) has been prepared by Technical Committee CEN/TC 189 "Geosynthetics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2014, and conflicting national standards shall be withdrawn at the latest by January 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 15382:2008.

Annex C provides details of significant technical changes between this European Standard and the previous edition.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive.

For relationship with EU Directive, see informative Annex ZA, which is an integral part of this document.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard allows manufacturers to describe geosynthetic barriers on the basis of declared values for characteristics relevant to the intended use and if tested to the specified method. It also includes procedures for evaluation of conformity and factory production control.

This European Standard may also be used by designers, end-users and other interested parties as a tool to define relevant and appropriate characteristics for specifications and on-site quality control. It should be emphasised however that not all characteristics and test methods quoted in this European Standard are suitable for the purpose of on-site quality control.

Tests for several non-mandated characteristics are still under study and will be included when the standard is revised.

The term "product" used in this standard refers to a geosynthetic barrier, including polymeric geosynthetic barriers, clay geosynthetic barriers and bituminous geosynthetic barriers.

This European Standard is part of a group of standards, addressing the requirements for geosynthetic barriers when used in a specific application.

Particular application cases may contain requirements about additional properties and – preferably standardised – test methods, if they are technically relevant and not conflicting with European Standards.

The design life of the product should be determined, since its function may be temporary, as a construction expediency, or permanent, for the lifetime of the structure.