საქართველოს სტანდარტი

სსკ: 25.220.60; 77.140.50

უწყვეტი ორგანული საფარით (ხვეულა საფარით) ფოლადის ბრტყელი პროდუქტები - მიწოდების ტექნიკური პირობები

საინფორმაციო მონაცემები

- **1** მიღებულია და დაშვებულია სამოქმედოდ: სსიპ-საქართველოს სტანდარტებისა და მეტროლოგიის ეროვნული სააგენტოს გენერალური დირექტორის 01/05/2023 წლის № 47 განკარგულებით
- **2 მიღებულია "თავფურცლის" თარგმნის მეთოდით:** სტანდარტიზაციის ევროპული კომიტეტის (ენ) სტანდარტი ენ 10169:2022 ,, უწყვეტი ორგანული საფარით (ხვეულა საფარით) ფოლადის ზრტყელი პროდუქტები მიწოდების ტექნიკური პირობები"

3 პირველად

4 რეგისტრირებულია: სსიპ-საქართველოს სტანდარტეზისა და მეტროლოგიის ეროვნული სააგენტოს რეესტრში: 01/05/2023 წლის №268-1.3-028917

წინამდებარე სტანდარტის ნებისმიერი ფორმით გავრცელება სააგენტოს ნებართვის გარეშე აკრძალულია

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 10169

March 2022

ICS 25.220.60; 77.140.50

Supersedes EN 10169:2010+A1:2012

English Version

Continuously organic coated (coil coated) steel flat products - Technical delivery conditions

Produits plats en acier revêtus en continu de matières organiques (prélaqués) - Conditions techniques de livraison

Kontinuierlich organisch beschichtete (bandbeschichtete) Flacherzeugnisse aus Stahl -Technische Lieferbedingungen

This European Standard was approved by CEN on 24 January 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents European foreword		Page
		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	6
4	Designation	12
5 5.1 5.2	Information to be supplied by the purchaser Mandatory information Options	14
6 6.1 6.2 6.3	RequirementsGeneralGeneral coating propertiesSpecial coating properties	15 17
6.4	Freedom of defects	
7 7.1 7.2	Inspection Types of inspection and inspection documents Test units	25
7.3 7.4 7.5 7.6	Type and number of tests Sampling Test methods Retests	26 26
8	Marking	31
9	Packing and dispatch	31
10	Storage	31
Anne	ex A (informative) Types of ambience	32
Anne	ex B (informative) Coating materials	35
Anne	ex C (informative) Outdoor exposure sites	37
Anne	ex D (informative) Storage	39
Bibli	ography	

European foreword

This document (EN 10169:2022) has been prepared by Technical Committee CEN/TC 459/SC 9 "Coated and uncoated flat products to be used for cold forming", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2022, and conflicting national standards shall be withdrawn at the latest by September 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10169:2010+A1:2012.

In comparison with the previous edition, the following technical modifications have been made:

- addition of the requirement about a maximum six-month duration between production and processing of the coil coated product;
- addition of the corrosion resistance category RC5+ corresponding to very high corrosivity category C5 combining RC5-I and RC5-M that have been removed from this document;
- addition of the UV resistance category R_{uv5} ;
- addition of third party supervision for natural weathering tests if a certificate is required by the purchaser;
- definition of a four-year test duration for corrosion resistance category RC5+;
- definition of requirements for natural outdoor UV radiation resistance tests;
- removal of Geleen from the list of natural outdoor corrosivity exposure sites;
- editorial improvements and updating of normative references.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.